


**WHAT IS CLAIMED IS:**

1. A method of making a fuser member having a support comprising the steps of:

A) providing a support;

B) coating from an organic solvent onto the support a coating composition comprising a fluorocarbon thermoplastic random copolymer, a curing agent having a bisphenol residue, a particulate filler containing zinc oxide, antimony-doped tin oxide particles and aminosiloxane, the fluorocarbon thermoplastic random copolymer having subunits of:



wherein

x is from 1 to 50 or 60 to 80 mole percent,

y is from 10 to 90 mole percent,

z is from 10 to 90 mole percent,

x + y + z equals 100 mole percent; and

C) curing the coating composition for 5 to 10 hours at a temperature in the range of 25°C to 275°C.

2. The method of claim 1 wherein the aminosiloxane is an amino functional polydimethyl siloxane copolymer.

3. The method of claim 2 wherein the amino functional polydimethyl siloxane copolymer comprises amino functional units selected from the group consisting of (aminoethylaminopropyl) methyl, (aminopropyl) methyl and (aminopropyl) dimethyl.

4. The method of claim 1 wherein the amino siloxane has a total concentration in the layer of from 1 to 20 parts by weight per 100 parts of the fluorocarbon thermoplastic random copolymer.



15. The method of claim 1 wherein the antimony-doped tin oxide particles have a total concentration of from 3 to 20 parts by weight per 100 parts of the fluorocarbon thermoplastic random copolymer.

16. The method of claim 1 wherein the antimony-doped tin oxide particles comprise 3 to 10 weight percent antimony.

17. The method of claim 1 wherein the fluorocarbon thermoplastic random copolymer further comprises a fluorinated resin.

18. The method of claim 17 wherein the fluorinated resin has a number average molecular weight of between 50,000 to 50,000,000.

19. The method of claim 17 wherein the ratio of fluorocarbon thermoplastic random copolymer to fluorinated resin is between 1 : 1 to 50 : 1.

20. The method of claim 17 wherein the fluorinated resin is polytetrafluoroethylene or fluoroethylenepropylene.

add  
a<sub>5</sub> 7